STEAM/AL

IT IMPIEGO

Tubo in gomma cord idoneo per mandata di acqua calda frammista a vapore in impieghi dove sia richiesta atossicità per i prodotti convogliati. Idoneo a sterilizzazione a vapore con punte fino a +164° C.

Normative di riferimento: **DM 21/3/73 e 18/6/79 + FDA.**

- **TEMPERATURA**: -40°C +120°C

STRUTTURA

- **Sottostrato**: liscio in gomma EPDM bianca alimentare resistente al calore.
- **Rinforzi**: inserzioni di fibre sintetiche ad alta resistenza.
- **Copertura**: in gomma EPDM blu resistente all'abrasione, al calore e agli agenti atmosferici. Stabilità del colore.
- **Superficie**: liscia ad impressione tela.
- **Marcatura**: listino scritta bianca "H.T. - STEAM/AL - W.P. 10 BAR (150 PSI) +120°C - FDA.

EN APPLICATION

Softwall rubber hose suitable for hot water and steam mix used where an atoxic hose is required. Suitable to scald with steam up to +164° C.

Standards: **DM 21/3/73 e 18/6/79 + FDA.**

- **TEMPERATURE RANGE:** -40°C +120°C

CONSTRUCTION

- **Tube**: white, smooth, heat resistant food quality EPDM rubber.
- **Reinforcement**: high strength synthetic textile plies.
- **Cover**: blue, abrasion, heat and weathering resistant EPDM rubber. Non staining.
- **Surface**: smooth fabric finished.
- **Branding**: white writing list "H.T. - STEAM/AL - W.P. 10 BAR (150 PSI) +120°C - FDA".

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESS. SCOPPIO BURST PRESSURE		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mt	ft
13	1/2"	23	29/32"	0.37	0.25	10	150	30	450	40	131
16	5/8"	26	1.1/32"	0.43	0.29	10	150	30	450	40	131
19	3/4"	30	1.1/16"	0.55	0.37	10	150	30	450	40	131
25	1"	37	1.15/32"	0.75	0.50	10	150	30	450	40	131

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.